

ASTERYA

COMPOSITION(iÇERİK): _____%76 PES %24 PP

WEIGHT(Gramaj)(g/m²): _____ 540±%5

MARTINDALE(Aşınma): _____ 15.000

SEAM SLIPPAGE(Dikiş Testi): _____warp:2.41mm/weft:3.39mm

TEAR STRENGTH(Yırtılma Mukavemeti): _____warp:211.76N /weft:197.43N

TENSILE STRENGTH(Kopma Mukavemeti): _____warp:1989.38N/weft:1543.20N

PILLING(Boncuklanma): _____4@5000revs

USAGE



Upholstered Furniture



Cushions



Curtains



Upholstered Headboards

CLEANING



Wash At Or Below
30°C



Do Not Bleach



Do Not Tumble Dry



Drip Dry In Shade



Dry Clean, Any Solvent,
Delicate



Hand Wash Normal