

## MANYAS

COMPOSITION(iÇERİK): ..... %87 PES %13 LIN  
WEIGHT(Gramaj)(g/m<sup>2</sup>): ..... 300±%5  
MARTINDALE(Aşınma): ..... 5.000  
SEAM SLIPPAGE(Dikiş Testi): ..... warp:3.59mm/weft:2.98mm  
TEAR STRENGTH(Yırtılma Mukavemeti): ..... warp:50.45N /weft:205.21N  
TENSILE STRENGTH: ..... warp:1180.82N/weft:1651.58N  
PILLING: ..... 4@5000revs

### USAGE



### CLEANING

