

PUFFY

COMPOSITION(iÇERİK): _____ %100PES

WEIGHT(Gramaj)(g/m²): _____ 380±%5

MARTINDALE(Aşınma): _____ 30.000

SEAM SLIPPAGE(Dikiş Testi): _____ warp:2.54mm/weft:3.46mm

TEAR STRENGTH(Yırtılma Mukavemeti): _____ warp:76.78N /weft:116.17N

TENSILE STRENGTH(Kopma Mukavemeti): _____ warp:1828.16N/weft:841.40N

PILLING(Boncuklanma): _____ 4-5@5000revs

USAGE



Upholstered Furniture



Cushions



Curtains



Upholstered Headboards

CLEANING



Wash At Or Below
30°C



Do Not Bleach



Do Not Tumble Dry



Drip Dry In Shade



Dry Clean, Any Solvent,
Delicate



Hand Wash Normal