

AKSU

COMPOSITION(iÇERİK): _____ %4 COT % 96PES

WEIGHT(Gramaj)(g/m²): _____ 460±%5

MARTINDALE(Aşınma): _____ 50.000

SEAM SLIPPAGE(Dikiş Testi): _____ warp:2.54mm/weft:3.38mm

TEAR STRENGTH(Yırtılma Mukavemeti): _____ warp:435.08N /weft:180.18N

TENSILE STRENGTH(Kopma Mukavemeti): _____ warp:2131.37N/weft:862.76N

PILLING(Boncuklanma): _____ 3-4@5000revs

USAGE



Upholstered Furniture



Cushions



Curtains



Upholstered Headboards

CLEANING



Wash At Or Below
30°C



Do Not Bleach



Do Not Tumble Dry



Drip Dry In Shade



Dry Clean, Any Solvent,
Delicate



Hand Wash Normal