


RONDA

COMPOSITION(iÇERİK): _____%58 PES%42 PP
WEIGHT(Gramaj)(g/m²): _____ 450±%5
MARTINDALE(Aşınma): _____ 40.000
SEAM SLIPPAGE(Dikiş Testi): _____ warp:2.74mm/weft:3.37mm
TEAR STRENGTH(Yırtılma Mukavemeti): _____ warp:140.02N /weft:143.99N
TENSILE STRENGTH(Kopma Mukavemeti): _____ warp:844.99N/weft:647.48N
PILLING(Boncuklanma): _____ 4-5@5000revs

USAGE



CLEANING

