

TUSKON

COMPOSITION(iÇERİK): _____%39 PES %61 PP

WEIGHT(Gramaj)(g/m²): _____ 280±%5

MARTINDALE(Aşınma): _____ 40.000

SEAM SLIPPAGE(Dikiş Testi): _____ warp:2.47mm/weft:3.04mm

TEAR STRENGTH(Yırtılma Mukavemeti): _____ warp:89.27N /weft:120.41N

TENSILE STRENGTH(Kopma Mukavemeti): _____ warp:989.14N/weft:533.24N

PILLING(Boncuklanma): _____ 4-5@5000revs

USAGE



Upholstered Furniture



Cushions



Curtains



Upholstered Headboards

CLEANING



Wash At Or Below
30°C



Do Not Bleach



Do Not Tumble Dry



Drip Dry In Shade



Dry Clean, Any Solvent,
Delicate



Hand Wash Normal